











HomeSure TileEX EX-11 CERAMIC EXPERT is a polymerized, grey cement-based powder tile adhesive with excellent application of ceramic and clay tiles. Tile that only requires clean water. Ideal for tiles with porosity above 3%.

#### COMPOSITION

- · Graded Sand · Cement · Selected Fillers
- Polymers

#### **COVERAGE**

workability, water resistant & slip resistant properties. It is designed for internal area adhesive **EX-11** is an easy-to-use adhesive

50-60 Sq. ft./ Bag(20kg) at 3 mm thickness on plain surface (or depending on substrate conditions). Minimum-Maximum thickness 3-12 mm.

# **FEATURES**



**Water Resistant** 



**Durable & Long Lasting** 



**Strong Bond** 



No Hacking Required

<u>IS 15477:2019</u> - Type 1

#### **TECHNICAL DATA**

**ADJUSTABILITY** 

#### **SPECIFICATIONS PARAMETERS OPEN TIME** 10 minutes

10 minutes

SLIP RESISTANCE · < 0.5 mm

POT LIFE 120 minutes approx

1.5 -1.9 g/ml DENSITY

#### MECHANICAL PROPERTIES

#### TENSILE ADHESION STRENGTH (After 28 days)

DRY CONDITION Minimum 0.5 N/mm<sup>2</sup>

#### SHEAR ADHESION STRENGTH (After 28 days)

Minimum 1 N/mm<sup>2</sup> DRY CONDITION





HomeSure TileEX EX-22 VITRIFIED EXPERT is a polymerized, grey cement-based powder tile adhesive with excellent workability, water resistant & slip resistant properties. It is designed for vitrified and semi vitrified tiles on interior wall and floor as well as for exterior floor application only. Tile adhesive EX-22 is an easy-to-use adhesive that only requires clean water. Ideal for tiles with porosity less than 3%.

#### COMPOSITION

- · Graded Sand · Cement · Selected Fillers
- Polymers

#### **COVERAGE**

50-60 Sq. ft./ Bag(20kg) at 3 mm thickness on plain surface (or depending on substrate conditions). Minimum-Maximum thickness 3-12 mm.

#### **TECHNICAL DATA**

#### **PARAMETERS SPECIFICATIONS**

**OPEN TIME** 15 minutes 15 minutes **ADJUSTABILITY** SLIP RESISTANCE < 0.5 mm

POT LIFE 120 minutes approx

DENSITY 1.5 -1.9 g/ml

#### **FEATURES**



**Water Resistant** 



Durable & Long Lasting



Strong Bond



No Hacking Required

IS 15477:2019 - Type 2

#### **MECHANICAL PROPERTIES**


#### TENSILE ADHESION STRENGTH (After 28 days)

DRY CONDITION Minimum 1.0 N/mm<sup>2</sup> WET CONDITION Minimum 1.0 N/mm<sup>2</sup>

#### SHEAR ADHESION STRENGTH (After 28 days)

DRY CONDITION Minimum 1.25 N/mm<sup>2</sup> HEAT AGING CONDITION Minimum 1.0 N/mm<sup>2</sup> WET CONDITION Minimum 1.0 N/mm<sup>2</sup>







HomeSure TileEX **EX-G 33 (GREY)** is a highly polymer enriched Portland cement based tile adhesive applicable for fixing all kinds of vitrified tiles, glass mosaic tiles, all types of natural stones, granite & dense, large dimension tiles & slabs. It is mainly suitable for tiles with an apparent porosity less than or equal to 3%. More demanding for wet & sub merged area.

HomeSure TileEX **EX-G 33** consisting of cement, graded sand and specialised polymers is made to have some unique properties, like high bond strength water retention, superior workability that can be useful for working in all types of internal wall and floor areas also on all types of external floor area.

#### **FEATURES**



**Water Resistant** 



**Durable & long lasting** 



No shrinkage



No Curing required

IS 15477:2019 - Type 2

#### COVERAGE

50-60 Sq. ft./ Bag(20kg) at 3 mm thickness on plain surface (Or depending on substrate conditions).

#### **TECHNICAL DATA**

**DENSITY** 

# PARAMETERS SPECIFICATIONS OPEN TIME : 20 Minutes ADJUSTIBILTY : 20 Minutes SLIP RESISTANCE : < 0.5 Mm POT LIFE : 120 Minutes approx

1.5 -1.9 g/ml

#### **MECHANICAL PROPERTIES**

#### **TENSILE ADHESION STRENGTH (After 28 Days)**

DRY CONDITION: Minimum 1.0 N/mm² WET CONDITION: Minimum 1.0 N/mm²

#### SHEAR ADHESION STRENGTH (After 28 Days)

DRY CONDITION: Minimum 1.25 N/mm<sup>2</sup>
HEAT AGING CONDITION: Minimum 1.0 N/mm<sup>2</sup>
WET CONDITION: Minimum 1.0 N/mm<sup>2</sup>







HomeSure TileEX **EX-33 STONE & GLASS EXPERT** is a polymerized, white cement-based powder tile adhesive with excellent workability, water resistant & slip resistant properties. This product is highly utilized for wet and submerged areas. It is suitable for vitrified tiles and natural stone in interior wall & floor applications as well as exterior floor application only. Tile adhesive **EX-33** is an easy-to-use adhesive that only requires clean water. Ideal for tiles with porosity less than 3%.

#### COMPOSITION

- · Graded Sand · Cement · Selected Fillers
- Polvmers

#### COVERAGE

50-60 Sq. ft./ Bag(20kg) at 3 mm thickness on plain surface (or depending on substrate conditions). Minimum-Maximum thickness 3-12 mm.

# TECHNICAL DATA

#### PARAMETERS SPECIFICATIONS

OPEN TIME : 20 minutes
ADJUSTABILITY : 20 minutes
SLIP RESISTANCE : < 0.5 mm

POT LIFE : 120 Minutes approx

DENSITY : 1.5 -1.9 g/ml

#### **FEATURES**



**Water Resistant** 



**Durable & Long Lasting** 



**Strong Bond** 



No Hacking Required

IS 15477:2019 - Type 2

#### **MECHANICAL PROPERTIES**

#### TENSILE ADHESION STRENGTH (After 28 days)

DRY CONDITION Minimum 1.0 N/mm² WET CONDITION Minimum 1.0 N/mm²

#### **SHEAR ADHESION STRENGTH** (After 28 days)

DRY CONDITION Minimum 1.25 N/mm²
HEAT AGING CONDITION Minimum 1.0 N/mm²
WET CONDITION Minimum 1.0 N/mm²







HomeSure TileEX EX-44 EXTERNAL EXPERT is a polymerized, grey cement-based powder tile adhesive with excellent workability, water resistant, slip resistant and extended open time properties. It can be used in wet, internal and external areas. It is suitable for all types of tiles and all natural stone. Tile adhesive **EX-44** is an easy-to-use adhesive that only requires clean

#### COMPOSITION

- · Graded Sand · Cement · Selected Fillers
- Polymers

#### COVERAGE

water. Ideal for tiles with porosity less than 3%.

50-60 Sq. ft./ Bag(20kg) at 3 mm thickness on plain surface (or depending on substrate conditions). Minimum- Maximum thickness 3-12 mm.

# **FEATURES**









IS 15477:2019 - Type 3

#### **TECHNICAL DATA**

#### **SPECIFICATIONS PARAMETERS**

35 minutes OPEN TIME **ADJUSTABILITY** 35 minutes SLIP RESISTANCE : < 0.5 mm

POT LIFE 120 Minutes approx

DENSITY 1.5 -1.9 a/ml

#### **MECHANICAL PROPERTIES**

#### TENSILE ADHESION STRENGTH (After 28 days)

DRY CONDITION Minimum 1.5 N/mm<sup>2</sup> WET CONDITION Minimum 1.0 N/mm<sup>2</sup>

#### **SHEAR ADHESION STRENGTH** (After 28 days)

DRY CONDITION Minimum 1.5 N/mm<sup>2</sup> HEAT AGING CONDITION Minimum 1.0 N/mm<sup>2</sup> Minimum 1.0 N/mm<sup>2</sup> WET CONDITION

#### **DEFORMABILITY** (After 28 days)

DEFORMABLE ADHESIVE (S1) ≥ 2.5 mm - < 5.0 mm









- · Cement base
- · Plywood
- Gypsum boards
- · Fibre cement boards

### **APPLICATION AREA**

- · All Tile on Tile applications
- · Interior & exterior floor & wall applications



HomeSure TileEX EX-55 ALL TILE EXPERT is a polymerized, white cement-based powder tile adhesive with excellent workability, water resistant, slip resistant and extended open time properties. It can be used in wet, internal and external areas and in commercial areas and workshops. It is suitable for all types of tiles and stone tiles on drywall board substrates. Tile adhesive EX-55 is an easy-to-use adhesive that only requires clean water. Ideal for tiles with porosity less than 3%.

#### **COMPOSITION**

- · Graded Sand · Cement · Selected Fillers
- Polymers

#### **COVERAGE**

50-60 Sq. ft./ Bag(20kg) at 3 mm thickness on plain surface (or depending on substrate conditions). Minimum- Maximum thickness 3-12 mm.

### **FEATURES**



**Water Resistant** 



**Durable & Long Lasting** 



**Strong Bond** 



No Hacking Required

IS 15477:2019 - Type 4

#### **TECHNICAL DATA**

SLIP RESISTANCE:

# PARAMETERS SPECIFICATIONS OPEN TIME : 35 minutes ADJUSTABILITY : 35 minutes

 $< 0.5 \, \text{mm}$ 

POT LIFE : 120 Minutes approx

DENSITY : 1.5 -1.9 g/ml

#### **MECHANICAL PROPERTIES**

#### TENSILE ADHESION STRENGTH (After 28 days)

DRY CONDITION Minimum 1.5 N/mm² WET CONDITION Minimum 1.0 N/mm²

#### SHEAR ADHESION STRENGTH (After 28 days)

DRY CONDITION Minimum 1.5 N/mm² HEAT AGING CONDITION Minimum 1.0 N/mm² WET CONDITION Minimum 1.0 N/mm²

#### **DEFORMABILITY** (After 28 days)

DEFORMABLE ADHESIVE (S1) ≥ 2.5 mm - < 5.0 mm



# इक्को का पांवर पैक टाईल साल्यूशन





अपने जगह की शान



Walplast Products Pvt. Ltd. ISO 9001: 2015 Certified Company Plot No A, 246, Cross Road Number 18, T.T.C. Industrial Area, MIDC Industrial Area, Mahape, Navi Mumbai, Maharashtra-400 710. FOLLOW US ON



SCAN FOR MORE DETAILS

